

BARKHAUSEN NOISE AND MAGNETOACOUSTIC EMISSION AS A POTENTIAL TOOLS FOR MECHANICAL PROPERTIES ESTIMATION OF FERROMAGNETIC MATERIALS

K. Makowska¹, Z.L. Kowalewski^{1,2}

¹ *Motor Transport Institute, Warsaw, Poland*

² *Institute of Fundamental Technological Research, Warsaw, Poland*

1. Introduction

It has been found that magnetic Barkhausen noise (MBE) and magnetoacoustic emission (MAE) are significantly sensitive to material damage, especially in the early stage of degradation [1-3]. The magnetic Barkhausen emission is defined as a voltage signal that is generated by the non-continuous domain walls movement in the magnetized material due to discontinues changes of the magnetic flux density [4]. In the case of steel the domain walls are of 180° and 90° types. Magnetic Barkhausen noise may be detected by both the contact probe and by the wound coil around the magnetized specimen. The movements of 90° magnetic domains generate the acoustic waves in materials having non-zero magnetostriction. The MAE may be detected by means of piezoelectric transducer. Due to the fact that elongation of antiparallel domains is the same, there are no acoustic waves coming from the 180° domain walls [4].

The aim of this work is an attempt for evaluation of mechanical properties variations by means of parameters calculated on the basis of measurements of Barkhausen noise, magnetoacoustic emission and magnetic hysteresis loop.

2. Investigation program

In the first step of experimental program, the first series of plain specimens made from power plant medium-carbon steel was subjected to creep process and the second series was subjected to plastic deformation in order to achieve material with increasing level of prestrain.

Subsequently, measurements of the magnetic Barkhausen signal, magnetoacoustic emission and determination of the hysteresis loop variations were carried out on the prestrained specimens.

After non-destructive tests the static tensile tests of pre-strained specimens were carried out in order to determine the basic mechanical parameters, e.g. yield point, ultimate tensile stress, etc. Relationships between the damage sensitive parameters coming from non-destructive and destructive tests are formulated.

3. Representative results

Analysis of the damage sensitive parameters reflects their different nature of changes (Fig. 1,2). Variations of the integral $\text{Int}(U_b)$ determined from envelopes of the Barkhausen noise and those of the yield point $R_{0,2}$ presented as a function of prior creep deformation exhibit a mirror image, i.e. when $\text{Int}(U_b)$ increased, $R_{0,2}$ decreased, and vice versa, Fig. 1.

Similar behaviour can be observed in the figure representing variations of the integral $\text{Int}(U_a)$, calculated from the magnetoacoustic emission envelopes, and yield point $R_{0,2}$ as a function of prior creep deformation, Fig.2.

4. Conclusions

Parameters coming from the rms envelopes of the Barkhausen noise and magnetoacoustic emission may provide complementary knowledge about mechanical properties variations caused by the history of deformation. It was observed that selected magnetic parameters are especially sensitive to damage development during the first two stages of creep.




Fig. 1. Variations of the integral calculated from MBE envelopes and yield point versus creep prestrain [5]




Fig. 2. Variations of the integral calculated from MAE envelopes and yield point versus creep prestrain

5. References

- [1] B. Augustyniak, L. Piotrowski, M. Chmielewski, M.J. Sablik (2007): Creep damage zone detection in exploited power plant tubes with magnetoacoustic emission, *Przełąd Elektrotechniczny*, **4**, 93-98
- [2] J.N. Mohopatra, A.K. Ray, J. Swaminathan, A. Mitra (2008): Creep behavior study of virgin and service exposed 5Cr-0.5Mo steel using magnetic Barkhausen emissions technique, *Journal of Magnetism and Magnetic Materials*, **320**, 2284-2290
- [3] K. Makowska K., Z.L. Kowalewski, B. Augustyniak, L. Piotrowski (2014): Determination of mechanical properties of P91 steel by means of magnetic Barkhausen emission, *Journal of Theoretical and Applied Mechanics*, **52**, 181-188
- [4] L. Piotrowski, B. Augustyniak, M. Chmielewski, I. Tomáš (2009): The influence of plastic deformation on magnetoacoustic properties of the CSN12021 grade steel, *Journal of Magnetism and Magnetic Materials*, **321**, 2331-2335
- [5] K. Makowska, Z.L. Kowalewski (2015): Possibilities of Barkhausen noise application for microstructure and mechanical properties evaluation [in Polish]. *Energetyka. Problemy energetyki i gospodarki paliwowo-energetycznej*, **736**, 664-667